

/ - -
 . . † . *
 , , *
 (2001 9 14)

Crystallization Behavior of Poly(ethylene terephthalate) /Ethylene-Methyl acrylate-Glycidyl methacrylate Copolymer Blend

Sang Youb Seong, Jong Kwan Lee, Kwang Hee Lee[†], and Byung Suk Jin^{*}

*Center for Advanced Functional Polymers, School of Chemical Science and Engineering,
Inha University, Inchon 402-751, Korea*

^{*}*Department of Applied Chemistry, Dongduk Women's University, Seoul 136-714, Korea*

[†]*e-mail : polylee@inha.ac.kr*

(Received September 14, 2001)

: ethylene - methyl acrylate - glycidyl methacrylate (E - MeA -
 GMA) poly(ethylene terephthalate) (PET)
 PET . PET E - MeA - GMA torque
 rheometer, FT - IR, SEM , DSC
 . X

ABSTRACT : The crystallization behavior of poly(ethylene terephthalate) (PET) /ethylene - methyl acrylate - glycidyl methacrylate copolymer (E - MeA - GMA) blend was studied. The extent of reaction and the reaction rate between PET and E - MeA - GMA were measured with torque rheometer, FT - IR and SEM. The effects of the grafting reaction on the crystallization behavior were investigated with DSC and time - resolved light scattering (TR - LS) techniques. The morphological change at the lamellar level was also examined by using a small angle X - ray scattering (SAXS) method.

Keywords : *poly(ethylene terephthalate), grafting reaction, crystallization, ethylene-methyl acrylate-glycidyl methacrylate copolymer.*

2-11

PET E - MeA - GMA가 PET
 ethylene - 가 . E -
 methyl acrylate - glycidyl methacrylate MeA - GMA PET E - MeA -
 (E - MeA - GMA) poly(ethylene terephthalate) GMA 가 /
 (PET)
 가 PET .
 .¹ E - MeA - GMA 가

/ - -
 , PET (15mm)
 / , 280 Mettler hot stage
 . / charge
 coupled device camera가
 가 ,
 가 180 .
 . PET E - MeA - DSC. DSC 280
 PET , 10 /min
 GMA E - MeA - GMA가 Perkin
 Elmer DSC - 7 .
 SAXS. 280 Mini - Max
 E - MeA - GMA가 .
 PET 180 oil bath 1
 (TR - LS), X (SAXS), 1.7
 mm , SAXS 가
 (beam line 4C1) .

Materials. 가 0.8 dL/g
 PET (TB - 180) . PET
 26000 g/mol 가
 52000 g/mol . PET E -
 MeA - GMA Atochem Latarder AX8920
 가 70/29/1 wt% .
 Torque Rheometer. PET E - MeA - GMA
 2:1 , Hakke rheometer
 280 , 60
 rpm , torque
 Twin Extruder. PET E - MeA - GMA
 2:1 , Bau - tech BA - 19
 barrel
 280 , screw 200 rpm,
 1 .
 FT-IR. Hot press 280 가 280 PET E - MeA - GMA
 3
 , 3 torque
 Elmer Model Spectrum 2000 . PET,
 TR-LS. cover glass E - MeA - GMA, (E - MeA -




Figure 1. Change in the mixing torque due to the grafting reaction.




Figure 3. Relative absorbance at 847 cm^{-1} as a function of reaction time.





Figure 2. FT-IR spectra of E-MeA-GMA, crystalline PET and amorphous PET samples.





GMA) - g - PET가
FT - IR

가 . Figure 2 PET, PET,
E - MeA - GMA IR , PET
(848 cm^{-1})¹⁴ E - MeA - GMA
(847 cm^{-1})가
PET

PET
. Figure 3

IR 가 847

torque rheometer FT - IR
PET PET
가 E - MeA - GMA
DSC
280 DSC
, 10 /min DSC
thermogram . Figure 5 DSC thermogram
PET 가



$$G = \frac{dR_s}{dt} \quad (2)$$

(analyzer) (polarizer)
H_v . Figure




Figure 6. H_v scattering patterns of the blend sample crystallized at 180 °C after annealing at 280 °C for 3 min. Crystallization time: (a) 10 s, (b) 25 s, (c) 75 s, and (d) 150 s.




Figure 7. Variation of spherulite growth rate (G) as a function of reaction time.

PET E - MeA - GMA가 PET

PET E - MeA - GMA
SAXS
Figure 8 (a) SAXS
profile
(L_C^M), (l_c), (l_a) Lorentz
corrected plot Fourier transform
.15, Figure 8 (b)
 L_C^M ,
 l_c
Figure 9 180
 L_C^M , l_c , l_a
 L_C^M ,
 l_a





Figure 8. (a) Raw SAXS profile and (b) normalized correlation function.

PET E - MeA - GMA

PET interlamellar PET

E - MeA - GMA가 interlamellar

PET E - MeA - GMA interlamellar interfibril

interfibril

PET

interlamellar E - MeA - GMA - g - PET




Figure 9. Structural parameters for the blend samples crystallized at 180 °C as a function of reaction time.

Torque rheometer,

FT - IR, SEM

280 5

PET E - MeA - GMA가 PET가 (Ia)

PET E - MeA - GMA interlamellar interfibril

1. D. R. Paul and S. Newman, "Polymer Blends", Academic Press, New York, 1978.
2. R. Fayl, R. Jerome, and Ph. Teyssie, *Makromol. Chem.*, 187, 837 (1986).
3. R. Fayl, R. Jerome, and Ph. Teyssie, *Polym. Eng. Sci.*, 27, 328 (1987).

4. J. Noolandi, *Polym. Eng. Sci.*, 24, 70 (1984).
5. J. Noolandi and K. M. Hong, *Macromolecules*, 15, 382 (1982).
6. J. Noolandi, *Makromol. Chem. Rapid Commun.*, 12, 517 (1991).
7. K. Shull and E. J. Kramer, *Macromolecules*, 23, 4769 (1990).
8. L. Leibler, *Makromol. Chem. Makromol. Symp.*, 16, 1 (1988).
9. M. Xanthos, "Reactive Extrusion : Principles and Practice", Hanser, New York, 1992.
10. M. Xanthos, *Polym. Eng. Sci.*, 28, 1392 (1988).
11. N. C. Liu and W. E. Baker, *Adv. Polym. Tech.*, 11, 249 (1992).
12. S. S. Dagli and K. M. Kamdar, *Polym. Eng. Sci.*, 34, 1709 (1994).
13. J. K. Kim and H. Lee, *Polymer*, 37, 305 (1996).
14. K. H. Lee and C. S. P. Sung, *Macromolecules*, 26, 3289 (1993).
15. G. R. Strobl, M. J. Schneider, and I. G. Voigt-Martin, *J. Polym. Sci., Polym. Phys. Ed.*, 18, 1361 (1980).