

가

† .

(2003 1 8 , 2003 5 3)

Synthesis of Ion Exchange Fiber Containing Amidoxime and Phosphoric Acid Groups and Its Uranium Adsorption Properties

Taek-Sung Hwang[†] and Jin-Won Park

Department of Chemical Engineering, Chungnam National University, Daejeon 305-764, Korea

[†]e-mail : tshwang@cuvic.cnu.ac.kr

(Received January 8, 2003; accepted May 3, 2003)

:
PP-g-(AN/Sty)
AN 가 , AN 가
AN 가 AN 40 vol% 45%
가 AN 가
50 가 가
9 wt% 5.8 mmol/g 가
가 0.5 N 가 ,
가

ABSTRACT : PP-g-(AN/Sty) was synthesized by grafting with acrylonitrile (AN) and styrene (Sty) onto PP staple fiber using an electron beam accelerator and followed by amidoximation and phosphorylation. Mole fraction of AN in the graft chain increased with the increase of the AN content in the monomer mixture. The highest AN grafting yield of 45% was obtained at a monomer ratio of 40 vol% AN/60 vol% Sty. Mole fraction of AN in the graft chain decreased with the increase of methanol amount used as solvent. As reaction temperature increased, the grafting yield of copolymer increased and reached equilibrium at 50 . Amount of amidoxime group in fibrous ion exchanger was increased as increasing amount of hydroxylamine, and the maximum content of amidoxime group was observed at 5.8 mmol/g with the 9 wt% hydroxylamine concentration. Content of phosphorous group in fibrous ion exchanger increased up to 0.5 N phosphoric acid concentration, and then leveled off. The adsorption ability of the copolymer for uranyl ion by the chelating adsorbents was in the following order : bifunctional PP-g-(AN/Sty) amidoximated PP-g-(AN/Sty) phosphorylated PP-g-(AN/Sty).

Keywords : irradiation grafting, comonomer, amidoximation, phosphorylation.

1.

가 가 가

14

5. (PP) (AN) (Sty) Junsei Chemical

(HA) (NH₂OH • HCl) (

PAC) Aldrich

() 1

Merck

uranyl nitrate [(UO₂)₃(NO₃)₃] • 6H₂O]

PP-g-(AN/Sty)

6. PP 10 g

60 PE

PE E-beam 가

20 Mrad PP

1 L

4

가 700 mL가

가

8

가

Table 1

12

가

60 (1)

Degree of grafting (%) = $\frac{W_1 - W_0}{W_0} \times 100$ (1)

가 , W₁ , W₀ PP

AN

11

(-COOH) 가

가

가 2

2.

(trunk polymer) ()

100 g/m², 20 μm

Table 1. Synthetic Conditions of PP-g-(AN/Sty) Co-polymer

Exp. No.	AN content in comonomer (vol%)	scontent in comonomer (vol%)	composition of Solvent (vol%)	reaction temperature ()	reaction time (hrs)
1	100	0			
2	80	20			
3	60	40	0, 20, 40,	30, 40 50,	5
4	40	60	60, 80	60, 70, 80	
5	20	80			
6	0	100			

CE Instrument (model : EA 1110)

가 (4) AN (2), (3),

$$W_{AN} = \text{AN weight in the graft chain} = \left(\frac{x_N}{100}\right) \times W_1 \left(\frac{53}{14}\right) \quad (2)$$

$$W_{Sty} = \text{Sty weight in the graft chain} = (W_1 - W_0) - W_{AN} \quad (3)$$

$$\text{Mole fraction of AN units} = (W_{AN}/53)/(W_{AN}/53 + W_{Sty}/104) \quad (4)$$

, W_0 , W_1 , W_{AN} , AN, W_{Sty} , Sty, x_N , 11.

. PP-g-(AN/Sty) [-CN(OH)(NH₂)]

Table 2

. HA NH₂OH · HCl NaOH, HCl

1 : 1(vol%)

13 60 24 (5), (6)

$$\text{Amount of amidoxime groups (mmol/g)} = \frac{W_2 - W_1}{W_2} \times 1000 \quad (5)$$

$$\text{Conversion in amidoximat ion} = \frac{(W_2 - W_1)/33}{(W_1 - W_0)/53} \times 100 \quad (6)$$

W_0 PP, W_1 W_2

Table 2. Amidoximation Conditions of PP-g-(AN/Sty) Copolymer

parameters	values
HA concentration (wt%)	3 ~ 9
cosolvent ratio in solution	methanol/H ₂ O = 1/1
reaction temperature ()	80
reaction time (hr)	12

Table 3. Condition of Phosphorylation

parameters	values
PAC concentration (N)	0.1, 0.3, 0.5, 1.0
benzene in solution (vol%)	60
reaction temperature ()	60
reaction time (hr)	3

. , 33 HA , 53 AN (-PO₃H)

Table 3

60 vol%가

. 2 soxhlet , 6 (7)

Amount of phosphoric acid groups (mmol/g) =

$$\frac{(W_2 \times W_1)/81}{W_2} \times 1000 \quad (7)$$

W_1 W_2 , 81

. 0.1 g 250 mL 0.1 N HCl 가 50 mL 24 10 mL 0.1 N NaOH (8)

$$\text{Capacity (meq/g)} = \frac{(V_{NaOH} \times N_{NaOH}) - 5 \times (V_{HCl} \times N_{HCl})}{\text{weight of fibrous ion exchanger}} \quad (8)$$

N_{HCl} HCl, N_{NaOH} V_{NaOH} NaOH mL

. 1 g 50 mL (9)

$$\text{Water uptake(\%)} = \frac{(W_w \times W_g)}{W_g} \quad (9)$$

$$W_g, W_w$$

3.

<i>E</i> -beam	PP	AN	Sty
		가 40 vol%	

PP-*g*-(AN/Sty)

가 Figure 1

Figure 1

60 vol%

60 vol%

Sty

PP

가 AN

Sty	가 PP
Sty	가

Figure 2 PP

AN

Sty

AN

. Figure 2

AN

가
가

AN

AN

AN

40 vol%

0.4




Figure 1. Grafting yield (%) of **Sty** and **AN** onto **PP** for various monomer content of **AN/Sty** (methanol 40 vol%, reaction temperature 50 °C, reaction time 5 hrs).

가 Sty 가 AN
AN PP

Figure 3 AN/Sty

. Figure 3

가

40 vol%

250%

AN Sty
가

가

PP

, 40 vol%

가




Figure 2. Relationship of mole fraction of AN in the graft chain, AN graft yield and AN content in the monomers (methanol 40 vol%, reaction temperature 50 °C, reaction time 5 hrs).




Figure 3. Grafting yield (%) of PP-*g*-(AN/Sty) graft copolymer for monomer content in solution (AN/Sty = 40/60, reaction temperature 50 °C, reaction time 5 hrs).

AN/Sty 40/60
AN
AN
가 Figure 4
가
AN 80 vol%
가 PP 가
Sty
AN 20 vol% 0.8




Figure 4. Relationship of mole fraction of AN in the graft chain, AN graft yield and methanol content in monomers (AN/Sty = 40/60, reaction temperature 50 °C, reaction time 5 hrs).




Figure 5. Grafting yield (%) of Sty and AN onto PP for various reaction temperature (AN/Sty = 30/70, methanol 40 vol%, reaction time 5 hrs).

Figure 5
PP-g-(AN/Sty)
Figure 5
50
250%

Figure 6
AN
Figure
6
AN
AN
AN 50
0.6
가 Sty
50
AN-Sty
250%
Table 4
5
HA PAc
Table 4
HA
가 가
가 ,
HA 5 wt%
10.6
Table 5




Figure 6. Relationship of mole fraction of AN in the graft chain, AN graft yield and AN content in the monomers (AN/Sty = 30/70, methanol 40 vol%, reaction time 5 hrs).

References

1. T. Hirotsu, A. Fujii, K. Sakane, S. Katoh, and K. Sugasaka, *Bull. Soc. Seawater Sci. Jpn.*, **35**, 16 (1981).
2. H. Egawa, M. Nakayama, T. Nonaka, and E. Sugihara, *J. Appl. Polym. Sci.*, **33**, 1993 (1988).
3. J. Okamoto, T. Sugo, A. Katakai, and H. Omichi, *J. Appl. Polym. Sci.*, **30**, 2967 (1985).
4. S. H. Choi and Y. C. Nho, *Radi. Phys. Chem.*, **57**, 187 (2000).
5. A. Chapiro, *Radiation Chemistry of Polymeric Systems*, Interscience, New York, 1962.
6. Y. C. Nho, J. L. Garnett, P. A. Dworjany, and H. C. Pyun, *Polymer(Korea)*, **16**, 115 (1992).
7. H. A. Abd El-Rehim, E. A. Hegazy, and A. El-Hag Ali, *Reac. Funct. Polym.*, **43**, 105 (2000).
8. El-Sayed A. Hegazy, H. A. Abd El-Rehim, and H. A. Shawky, *Radi. Phys. Chem.*, **57**, 85 (2000).
9. H. Egawa, *Polym. Proc. Jap.*, **32**, 38 (1983).
10. D. W. Jeon, *J. Kor. Fiber Soc.*, **23**, 65 (1986).
11. T. Kawai, K. Saito, K. Sugita, T. Kawakami, J. Kanno, A. Katakai, N. Seko, and T. Sugo, *Radi. Phys. Chem.*, **59**, 405 (2000).
12. K. S. Huh and G. S. Suh, *J. Kor. Inst. Chem. Eng.*, **29**, 63 (1991).
13. S. H. Choi and Y. C. Nho, *Radi. Phys. Chem.*, **58**, 187 (2000).
14. Y. G. Chin and S. C. Choi, *J. Kor. Soc. Clothing Textile*, **13**, 128 (1989).